



Product Data Sheet

OK 55.00

E 'Manual metal-arc welding'
ESAB AB Sweden

Signed by P-O Oskarsson	Approved by Tony Dray/Christos Skodras	Reg no EN005191	Cancelling EN004777	Reg date 2010-02-16	Page 1 (2)
----------------------------	---	--------------------	------------------------	------------------------	---------------

REASON FOR ISSUE

AWS data updated


GENERAL

Basic, high quality electrode for welding high strength mild steels. Good impact strength and resistance to hot cracking.

Min AC OCV: 65
Polarity: AC, DC+

Alloy Type: Carbon Manganese
Coating Type: Lime Basic
Diff Hydrogen: <4.0 ml/100g

WELDING POSITIONS



CLASSIFICATIONS Electrode

SFA/AWS A5.1	E7018-1H4 R
CSA W48	E4918-1
EN ISO 2560-A	E 46 5 B 32 H5

APPROVALS

ABS	3YH5
BV	3Y H5
CE	EN 13479
CWB	CSA W48
DB	10.039.03
DNV	4 YH5
GL	3YH5
LR	3, 3Y H5
RS	3YH5
VdTÜV	00632

CHEMICAL COMPOSITION

All Weld Metal (%)

	Min	Max
C	0.05	0.10
Si	0.30	0.70
Mn	1.10	1.60
P		0.030
S		0.030
Cr		0.1
Ni		0.1
Mo		0.1
V		0.03
Nb		0.02
Cu		0.1
Al		0.03
Sn		0.01
Ti		0.03
Pb		0.02
As		0.03

PROLINE
professional welding supplies



Product Data Sheet

OK 55.00

E 'Manual metal-arc welding'
ESAB AB Sweden

Signed by P-O Oskarsson	Approved by Tony Dray/Christos Skodras	Reg no EN005191	Cancelling EN004777	Reg date 2010-02-16	Page 2 (2)
----------------------------	---	--------------------	------------------------	------------------------	---------------

MECHANICAL PROPERTIES OF WELD METAL

Properties	ISO		AWS
	As welded Min	Max	As welded Min
Rp0.2 (MPa)			400
ReL (MPa)	460		
Rm (MPa)	560	660	490
A4 (%)			22
A5 (%)	22		
Charpy V at -45°C (J)			27
Charpy V at -50°C (J)	47		

ECONOMICS & CURRENT DATA

Dimension (mm)	Current (A)		W	η	N	B	H	T	U	Welding Positions
\varnothing x Length	Min	Max								
2.5 x 350	80	110	2.38	127	0.64	65.8	0.86	63.5	22.6	1,2,3,4,6
3.2 x 350	110	140	3.9	126	0.62	41.1	1.22	72	22.6	1,2,3,4,6
3.2 x 450	110	140	5.0	125	0.69	30.0	1.40	88	24	1,2,3,4,6
4.0 x 350	140	200	5.8	121.7	0.62	28	1.77	72.5	23.2	1,2,3,4,6
4.0 x 450	140	200	7.4	125	0.70	19.0	2.00	94	24	1,2,3,4,6
5.0 x 450	200	270	10.8	125	0.72	13.0	3.00	94	24	1,2,3,4
6.0 x 450	215	360	12.6	125	0.72	9.0	4.00	98	25	1,2,3

- W** = Weight (kg / 100 electrodes)
 η = Efficiency (g weld metal x 100 / g core wire)
N = Effective value (kg weld metal / kg electrodes)
B = Changes (number of electrodes / kg weld metal)
H = Deposit rate at 90% of max current (kg weld metal / hour arc time)
T = Fusion time at 90% of max current (s / electrode)
U = Arc voltage (V)

OTHER DATA

Applications:

Manual metal arc welding of carbon steels, carbon manganese steels and fine grained carbon manganese steels with elevated yield strength.

Core wire:

P < 0.015%

S < 0.015 %

N < 100 ppm

PROLINE
professional welding supplies