STRATA 350 – Special bronze welding electrode

SUPERIOR PRODUCTS FOR MAINTENANCE AND REPAIR

STRATA INTERNATIONAL LTD.

FEATURES & APPLICATIONS

For joining a wide variety of copper base alloys to themselves and to steels and cast irons.

AC-DC tin bronze electrode can be used as an electric brazing rod.

- Bronze electrode that works very well on AC current
- Excellent for joining copper base alloys not only to themselves but to stainless steel, cast iron and steels

ALL WELD METAL ANALYSIS (TYPICAL WEIGHT %)

Microstructure: A multi phase copper base structure with complete eutectoids

Flux Colour: Dark Brown

			-	5	3 2 2 (
Sn	Fe	Р	Al	Mn	Pb	Si	Ni	Other	Cu
8	.1	.1	.01	.01	.02	.05	.05	.50	Bal

TYPICAL MECHANICAL PROPERTIES

Undiluted Weld Metal

Tensile Strength Yield Strength Elongation Hardness Maximum Value Up To 50,000 PSI (340 MPa) 30,000 PSI (210 MPa) 18% Brinell 105, Rockwell B78



Ph: 0800 699 353 sales@prolinewelding.com

WELDING CURRENT & INSTRUCTIONS

Recommended Current: DC Straight (-) or AC

Diameter (mm)	3/32 (2.5)	1/8 (3.25)	5/32 (4.0)
Minimum Amperage	75	100	120
Maximum Amperage	105	135	160

Welding Techniques: Remove all surface contamination from weld area. Maintain a short arc gap and fill in craters prior to extinguishing the arc.

Welding Positions: Flat

Deposition Rates:

Diameter	Length	Weldmetal/	Electrodes per	Arc Time Of	Amperage
	()	_, _, _,			• ···•
(mm)	(mm)	Electrode	lb (kg) of	Deposition	Settings
			Weldmetal	min/lb (kg)	
3/32 (2.5	14" (350)	.6oz (17g)	27 (59)	54 (118)	85
1/8 (3.25)	14" (350)	.7oz (20g)	22 (48)	38 (83)	120
5/32 (4.0)	14" (350)	1oz (28g)	15 (32)	20 (45)	140

APPROXIMATE ELECTRODE PACKAGING & DIMENSIONS

Diameter (mm)	1/8 (3.25)	5/32 (4.0)	3/16 (5.0)
Length (mm)	14" (350)	14" (350)	14" (350)
Electrodes/lb	22	14	9
Electrodes/kg	48	31	20