



STRATA INTERNATIONAL LTD.

SUPERIOR PRODUCTS FOR MAINTENANCE AND REPAIR

STRATA GT4 – Electrode for chamfering and gouging all types of metals

INTERNATIONAL CLASSIFICATIONS

NONE APPLICABLE TO THIS PROPRIETARY PRODUCT

FEATURES & APPLICATIONS

Can gouge, bevel or cut all metals including stainless steels, aluminiums and copper. Excellent for the removal of stainless steel joints and overlays. No oxygen is required.

Chamfering/cutting electrode with 25% more arc blast force

- A grey flux coated electrode for extra-low smoke and piercing
- Special coating elements form an electrically conductive “cup” for ease of restrike
- Designed specifically for small AC welding machines

ALL WELD METAL ANALYSIS (TYPICAL WEIGHT %)

Flux Colour: Grey

These electrodes do not make deposits

WELDING CURRENT & INSTRUCTIONS

Recommended Current: DC Straight (-) or AC

Diameter (mm)	3/32 (2.5)	1/8 (3.25)	5/32 (4.0)	3/16 (5.0)
Minimum Amperage	100	170	220	300
Maximum Amperage	170	250	330	450

Welding Techniques: Hold electrode at a 10° angle above workpiece. Initiate arc and move forward in a straight or back and forth motion. For cutting use a “sawing action” technique.

Welding Positions: Flat, Vertical up, Vertical down, Horizontal, Overhead

PROLINE
professional welding supplies

Ph: 0800 699 353
sales@prolinewelding.com



STRATA INTERNATIONAL LTD.

SUPERIOR PRODUCTS FOR MAINTENANCE AND REPAIR

Gouging Rates:

Diameter (mm)	Length (mm)	Arc Time of Gouging SEC/in (mm)	Weight of Gouged Metal g/min	Amperage Setting
3/32 (2.5)	14" (350)	1.6 (.064)	35	160
1/8 (3.2)	14" (350)	1.2 (.048)	100	230
5/32 (4.0)	14" (350)	1.0 (.04)	120	310
3/16 (5.0)	14" (350)	.8 (.032)	180	420

APPROXIMATE ELECTRODE PACKAGING & DIMENSIONS

Diameter (mm)	3/32 (2.5)	1/8 (3.25)	5/32 (4.0)	3/16 (5.0)
Length (mm)	14" (350)	14" (350)	14" (350)	14" (350)
Electrodes/lb	24	14	9	8
Electrodes/kg	53	31	20	18